

## **Product Specification – AXG19 Uniaxial Geogrid**

**DISCLAIMER:** Alliance Geosynthetics reserves the right to change its product specifications at any time and without notice. It is the user's responsibility to ensure that this specification is current and that the specified product is appropriate for the application being considered.

Product Type: High molecular weight, knitted and coated, high tenacity yarns

Composition: Polyester with polymeric coating

## **Product Properties**

•	Test method	Units	MD value <sup>1</sup>
Mechanical Properties			
Ultimate tensile strength	ASTM D 6637-10 (Method A)	lb/ft	3,600
<ul> <li>Creep limited strength</li> </ul>	ASTM D 5262 and D6992	lb/ft	2,323
<ul> <li>Long-term design strength<sup>1</sup></li> </ul>	ASTM D 5262 and D6992	lb/ft	1,919
		Units	Value
Physical Properties			
<ul> <li>Roll dimensions<sup>2</sup></li> </ul>		ft	6 x 300
<ul> <li>Mass per unit area</li> </ul>		oz/SY	6.5
<ul> <li>Approximate roll weight<sup>3</sup></li> </ul>		lbs	95

## Notes:

- 1. Values based on use of geogrids in sand, silt or clay backfill
- 2. Rolls with 12 ft widths are also available
- 3. Roll weights represent average values including shipping cores. Actual roll weights may vary
- 4. Structural designs using these products should be carried out by a licensed design engineer
- 5. Alliance Geosynthetics, LLC assumes no liability whatsoever for the accuracy or completeness of this information or for the use of this information by the purchaser. This document should not be construed as providing engineering advice or recommendations